



Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

OSAKA OFFICE:6-1-124,NISHIKUJYO,KONOHANA-KU,OSAKA 554-0012 JAPAN
TEL No.06-6466-6690 FAX No.06-6466-7797



For more or latest information please consult DNT

Aug. 2006

FEATURES: <ul style="list-style-type: none">· Zero VOC· Low Odor· Excellent Workability.· Good Hiding Power· For Inside Coating	NO./NAME :
	NO VOC CLEAN
	TYPE :
	Acrilic Emulsion Paint.
	SHIPPING WEIGHT :
	16kg

SPECIFICATION DATA

PACKAGE	1 Component
COLOR	Full Range Colors
FINISH	Flat
SPECIFIC GRAVITY at 20	Material : 1.53 Volatiles : 1.00
VISCOSITY at 20	90 ~ 100 Krebs Units
SOLIDS CONTENT	58 ~ 63% - by weight
DRYING TIME	at 5 at 20 at 30 (41° F) (68° F) (68° F)
	To Touch : 30 20 15 (minutes)
	Tack Free : 120 60 45 (minutes)
	The recoating time is specified in the application instructions.
RECOMMENDED DRY FILM THICKNESS PER COAT	20 ~ 30 Microns
FLASH POINT	-
SHELF LIFE at 20	1 Year

DNT Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

NO VOC CLEAN

APPLICATION INSTRUCTIONS

SURFACE PREPARATION	See Note 1			
APPLICATION METHOD	Brush, Roller, Spray			
THINNER REQUIRED	Clean Fresh Water			
DILUTION RATIO	<u>By Brush, Roller</u> 5 ~ 15%	<u>By Spray</u> 20 ~ 30%		
RECOMMENDED FILM THICKNESS PER COAT	Dry: 20 ~ 30 μ Wet: -			
COATING INTERVALS		at 5 (41° F)	at 20 (68° F)	at 30 (68° F)
	Min:	3	2	1.5 (hours)
	Max:	-	-	-

NOTES

1. Remove completely all dirt, grease, oil, or other contaminants from surface to be coated.
2. Stir thoroughly the material until it is of uniform constituency prior to application.