



# Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

OSAKA OFFICE:6-1-124,NISHIKUJYO,KONOHANA-KU,OSAKA 554-0012 JAPAN  
TEL No.06-6466-6690 FAX No.06-6466-7797



For more or latest information please consult DNT

Dec. 2004

FEATURES:  · Low Odor.	NO./NAME :
	<b>NO VOC CLEAN SEALER</b>
	TYPE :
	Acrylic Resin Sealer.
	SHIPPING WEIGHT :
	15kg

## SPECIFICATION DATA

PACKAGE	1 Component
COLOR	White
FINISH	-
SPECIFIC GRAVITY at 20	Material : 1.37 Volatiles: 1.0
VISCOSITY at 20	80 Krebs Units
SOLIDS CONTENT	50-55% - by weight
DRYING TIME	at 5      at 20      at 30 (41° F)    (68° F)    (68° F)
	To Touch :      60      30      20      (minutes)
	Tack Free :      4      2      1.5      (hours)
	The recoating time is specified in the application instructions.
RECOMMENDED DRY FILM THICKNESS PER COAT	-
FLASH POINT	-
SHELF LIFE at 20	1 Year

# DNT Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

NO VOC CLEAN SEALER

---

## APPLICATION INSTRUCTIONS

SURFACE PREPARATION	See Note 1				
APPLICATION METHOD	Brush, Roller,Airless Spray				
THINNER REQUIRED	Clean Fresh Water				
DILUTION RATIO	<u>By Brush, Roller</u> 10-20%	<u>By Airless Spray</u> 20-30%			
RECOMMENDED FILM THICKNESS PER COAT	Dry: - Wet: -				
COATING INTERVALS		at 5 (41° F)	at 20 (68° F)	at 30 (68° F)	
	Min:	4	3	2	(hours)
	Max:	1	1	1	(months)

### NOTES

1. Remove completely all dirt,grease,oil,or other contaminants from surface to be coated.
2. Stir thoroughly the material until it is of uniform constituency prior to application.