



# Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

OSAKA OFFICE:6-1-124,NISHIKUJYO,KONOHANA-KU,OSAKA 554-0012 JAPAN  
TEL No.06-6466-6690 FAX No.06-6466-7797



For more or latest information please consult DNT

Oct. 2007

FEATURES: <ul style="list-style-type: none"><li>· Safety is good in a water system.</li><li>· Good Stain Blocking.</li><li>· Good Water and Weather Resistance.</li><li>· Good Workability and Smooth Finishing .</li></ul>	NO./NAME :
	<b>SUISEI BUILDEC FLAT</b>
	TYPE :
	Acrilic Emulsion Paint.
	SHIPPING WEIGHT :
	16kg

## SPECIFICATION DATA

PACKAGE	1 Component
COLOR	Full Range Colors
FINISH	Flat
SPECIFIC GRAVITY at 20	Material : 1.45 Volatiles: 1.00
VISCOSITY at 20	90 ~ 110 Krebs Units
SOLIDS CONTENT	55 ~ 65% - by weight
DRYING TIME	at 5 at 20 at 30 (41° F) (68° F) (86° F)
	To Touch : 120 60 30 (minutes)
	Tack Free : 4 2 1 (hours)
	The recoating time is specified in the application instructions.
RECOMMENDED DRY FILM THICKNESS PER COAT	20 ~ 30 Microns
FLASH POINT	-
SHELF LIFE at 20	1 Year

# DNT Product Data Sheet

# UNI Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

SUISEI BUILDEC FLAT

---

## APPLICATION INSTRUCTIONS

SURFACE PREPARATION	See Note 1			
APPLICATION METHOD	Brush, Roller, Spray			
THINNER REQUIRED	Clean Fresh Water			
DILUTION RATIO	<u>By Brush, Roller</u> 5 ~ 15%	<u>By Spray</u> 10 ~ 20%		
RECOMMENDED FILM THICKNESS PER COAT	Dry: 20 ~ 30 $\mu$ Wet: -			
COATING INTERVALS		at 5 (41° F)	at 20 (68° F)	at 30 (86° F)
	Min:	6	3	2 (hours)
	Max:	-	-	-

### NOTES

1. Remove completely all dirt, grease, oil, or other contaminants from surface to be coated.
2. Stir thoroughly the material until it is of uniform constituency prior to application.