



# Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

OSAKA OFFICE:6-1-124,NISHIKUJYO,KONOHANA-KU,OSAKA 554-0012 JAPAN  
TEL No.06-6466-6690 FAX No.06-6466-7797



For more or latest information please consult DNT

Jul. 2006

<b>FEATURES:</b> <ul style="list-style-type: none"> <li>· Energy Saving.</li> <li>· Long Lasting.</li> <li>· Excellent Weather Resistance.</li> <li>· Type of Mild Solvent.</li> </ul>	<b>NO./NAME :</b>  <p style="text-align: center;"><b>ECO-COOL MILD F</b></p>
	<b>TYPE :</b>  <p style="text-align: center;">Fluorocarbon Resin Paint.</p>
	<b>SHIPPING WEIGHT :</b>  <p style="text-align: center;">15kg Unit(13.5kg Base,1.5kg Hardener)</p>

## SPECIFICATION DATA

PACKAGE	2 Component			
COLOR	Full Range Colors			
FINISH	Gloss			
SPECIFIC GRAVITY at 20	Material : 1.22 Volatiles: 0.80			
VISCOSITY at 20	105 Krebs Units			
SOLIDS CONTENT	64% - by weight			
DRYING TIME	at 5 (41° F)	at 20 (68° F)	at 30 (68° F)	
	To Touch :	120	60	30 (minutes)
	Tack Free :	16	8	6 (hours)
	The recoating time is specified in the application instructions.			
RECOMMENDED DRY FILM THICKNESS PER COAT	30 Microns			
FLASH POINT	Base : 41.0	(106 ° F)		
	Hardener : 40.0	(104 ° F)		
SHELF LIFE at 20	1 Year			

# DNT Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

ECO-COOL MILD F

---

## APPLICATION INSTRUCTIONS

SURFACE PREPARATION	See Note 1															
APPLICATION METHOD	Brush, Roller,Airless Spray															
THINNER REQUIRED	PAINT THINNER															
DILUTION RATIO	<u>By Brush, Roller</u> <u>By Airless Spray</u> 5 ~ 10%                      10 ~ 20%															
RECOMMENDED FILM THICKNESS PER COAT	Dry: 30 microns Wet: -															
COATING INTERVALS	<table><thead><tr><th></th><th>at 5 (41° F)</th><th>at 20 (68° F)</th><th>at 30 (68° F)</th><th></th></tr></thead><tbody><tr><td>Min:</td><td>24</td><td>16</td><td>12</td><td>(hours)</td></tr><tr><td>Max:</td><td>7</td><td>7</td><td>5</td><td>(days)</td></tr></tbody></table>		at 5 (41° F)	at 20 (68° F)	at 30 (68° F)		Min:	24	16	12	(hours)	Max:	7	7	5	(days)
	at 5 (41° F)	at 20 (68° F)	at 30 (68° F)													
Min:	24	16	12	(hours)												
Max:	7	7	5	(days)												

### NOTES

1. Remove completely all dirt,grease,oil,or other contaminants from surface to be coated.
2. Stir thoroughly the material until it is of uniform constituency prior to application.