



Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

OSAKA OFFICE:6-1-124,NISHIKUJYO,KONOHANA-KU,OSAKA 554-0012 JAPAN
TEL No.06-6466-6690 FAX No.06-6466-7797



For more or latest information please consult DNT

Jun. 2006

FEATURES: · Excellent Workability. · Good Water Resistance.	NO./NAME :
	SUISEI YUKA COAT
	TYPE : Acrylic Resin Paint.
	SHIPPING WEIGHT : 16kg , 4kg

SPECIFICATION DATA

PACKAGE	1 Component
COLOR	Full Range Colors
FINISH	Flat
SPECIFIC GRAVITY at 20	Material : 1.22 Volatiles : 1.00
VISCOSITY at 20	80 ~ 100 Krebs Units
SOLIDS CONTENT	45 ~ 50% - by weight
DRYING TIME	at 5 at 20 at 30 (41° F) (68° F) (86° F)
	To Touch : 60 20 15 (minutes)
	Tack Free : 240 60 45 (minutes)
	The recoating time is specified in the application instructions.
RECOMMENDED DRY FILM THICKNESS PER COAT	-
FLASH POINT	-
SHELF LIFE at 20	1 Year

DNT Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

SUISEI YUKA COAT

APPLICATION INSTRUCTIONS

SURFACE PREPARATION	See Note 1				
APPLICATION METHOD	Brush, Roller, Spray				
THINNER REQUIRED	Clean Fresh Water				
DILUTION RATIO	<u>By Brush, Roller</u> 5 ~ 10%	<u>By Spray</u> 5 ~ 10%			
RECOMMENDED FILM THICKNESS PER COAT	Dry: - Wet: -				
COATING INTERVALS		at 5 (41° F)	at 20 (68° F)	at 30 (86° F)	
	Min:	6	2	1.5	(hours)
	Max:	1	1	1	(months)

NOTES

1. Remove completely all dirt, grease, oil, or other contaminants from surface to be coated.
2. Stir thoroughly the material until it is of uniform constituency prior to application.