



# Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

OSAKA OFFICE:6-1-124,NISHIKUJYO,KONOHANA-KU,OSAKA 554-0012 JAPAN  
TEL No.06-6466-6690 FAX No.06-6466-7797



For more or latest information please consult DNT

Aug. 2006

FEATURES:  · Good Water Resistance.  · Good Alkali Resistance.	NO./NAME :
	<b>YUKA COAT ACRYL</b>
	TYPE :
	Acrylic Resin Paint.
	SHIPPING WEIGHT :
	16kg , 4kg

## SPECIFICATION DATA

PACKAGE	1 Component
COLOR	Full Range Colors
FINISH	Gloss
SPECIFIC GRAVITY at 20	Material : 1.20 Volatiles : 0.85
VISCOSITY at 20	90 ~ 110 Krebs Units
SOLIDS CONTENT	53 ~ 58% - by weight
DRYING TIME	at 5      at 20      at 30 (41° F)    (68° F)    (68° F)
	To Touch :      40      15      10      (minutes)
	Tack Free :      180      40      30      (minutes)
	The recoating time is specified in the application instructions.
RECOMMENDED DRY FILM THICKNESS PER COAT	20 Microbs
FLASH POINT	19 (67 ° F)
SHELF LIFE at 20	1 Year

# DNT Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

YUKA COAT ACRYL

---

## APPLICATION INSTRUCTIONS

SURFACE PREPARATION	See Note 1															
APPLICATION METHOD	Brush , Roller , Spray															
THINNER REQUIRED	VINYOSE THINNER A															
DILUTION RATIO	<u>By Brush , Roller</u> 100%															
RECOMMENDED FILM THICKNESS PER COAT	Dry: 20 Microns Wet: -															
COATING INTERVALS	<table><thead><tr><th></th><th>at 5 (41° F)</th><th>at 20 (68° F)</th><th>at 30 (68° F)</th><th></th></tr></thead><tbody><tr><td>Min:</td><td>4</td><td>2</td><td>1.5</td><td>(hours)</td></tr><tr><td>Max:</td><td>-</td><td>-</td><td>-</td><td></td></tr></tbody></table>		at 5 (41° F)	at 20 (68° F)	at 30 (68° F)		Min:	4	2	1.5	(hours)	Max:	-	-	-	
	at 5 (41° F)	at 20 (68° F)	at 30 (68° F)													
Min:	4	2	1.5	(hours)												
Max:	-	-	-													

## NOTES

1. Remove completely all dirt,grease,oil,or other contaminants from surface to be coated.
2. Stir thoroughly the material until it is of uniform constituency prior to application.