



Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

OSAKA OFFICE:6-1-124,NISHIKUJYO,KONOHANA-KU,OSAKA 554-0012 JAPAN
TEL No.06-6466-6690 FAX No.06-6466-7797



For more or latest information please consult DNT

Jun. 2006

FEATURES: · Good Elastic Type. · Excellent Adhesiveness. · Finishing Coat of Various Pattern.	NO./NAME : DNT DANSEI FILLER ICHIEKI TEKUTO MAX
	TYPE : Slight Elastic Filler of Water Based Cross-linking Type at Normal Temperature.
	SHIPPING WEIGHT : 16kg

SPECIFICATION DATA

PACKAGE	1 Component
COLOR	White
FINISH	-
SPECIFIC GRAVITY at 20	Material : 1.50 Volatiles : 1.00
VISCOSITY at 20	60000mPa.s(BH Type)
SOLIDS CONTENT	75 ~ 85% - by weight
DRYING TIME	at 5 at 20 at 30 (41° F) (68° F) (68° F)
	To Touch : 6 3 2 (hours)
	Tack Free : 20 10 8 (hours)
	The recoating time is specified in the application instructions.
RECOMMENDED DRY FILM THICKNESS PER COAT	-
FLASH POINT	-
SHELF LIFE at 20	1 Year

DNT Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

DNT DANSEI FILLER ICHIEKI TEKUTO MAX

APPLICATION INSTRUCTIONS

SURFACE PREPARATION	See Note 1				
APPLICATION METHOD	Roller , Spray				
THINNER REQUIRED	Clean Fresh Water				
DILUTION RATIO	<u>By Roller</u> 0 ~ 3%	<u>By Spray</u> 0 ~ 3%			
RECOMMENDED FILM THICKNESS PER COAT	Dry: - Wet: -				
COATING INTERVALS		at 5 (41° F)	at 20 (68° F)	at 30 (68° F)	
	Min:	24	16	12	(hours)
	Max:	7	7	7	(days)

NOTES

1. Remove completely all dirt,grease,oil,or other contaminants from surface to be coated.
2. Stir thoroughly the material until it is of uniform constituency prior to application.