



# Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

OSAKA OFFICE:6-1-124,NISHIKUJYO,KONOHANA-KU,OSAKA 554-0012 JAPAN  
TEL No.06-6466-6690 FAX No.06-6466-7797



For more or latest information please consult DNT

Aug. 2006

FEATURES: <ul style="list-style-type: none"><li>· Excellent Workability.</li><li>· Good Alkali Resistance.</li><li>· Good Water Resistance.</li></ul>	NO./NAME :
	<b>MIGHTY EPO SEALER WHITE</b>
	TYPE :
	Two-component Epoxy Resin Sealer With Good Adhesion and Chemical Resistance and Base Stiffening Capability.
	SHIPPING WEIGHT :
	16kg

## SPECIFICATION DATA

PACKAGE	2 Component
COLOR	White
FINISH	-
SPECIFIC GRAVITY at 20	Material : 1.35 Volatiles : 0.85
VISCOSITY at 20	80 ~ 100 Krebs Units
SOLIDS CONTENT	63 ~ 68% - by weight
DRYING TIME	at 5      at 20      at 30 (41° F)    (68° F)    (68° F)
	To Touch :      180      60      30      (minutes)
	Tack Free :      24      8      6      (hours)
	The recoating time is specified in the application instructions.
RECOMMENDED DRY FILM THICKNESS PER COAT	20 Microns
FLASH POINT	BASE : 26 (79 ° F) HARDNER : 23 (73 ° F)
SHELF LIFE at 20	1 Year

# DNT Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

MIGHTY EPO SEALER WHITE

---

## APPLICATION INSTRUCTIONS

SURFACE PREPARATION	See Note 1															
APPLICATION METHOD	Brush , Roller , Spray															
THINNER REQUIRED	EPONICS THINNER A															
DILUTION RATIO	<u>By Brush , Roller</u> <u>By Spray</u> 5 ~ 10%                      10 ~ 20%															
RECOMMENDED FILM THICKNESS PER COAT	Dry: 30 $\mu$ Wet: 75 $\mu$															
COATING INTERVALS	<table><thead><tr><th></th><th>at 5 (41° F)</th><th>at 20 (68° F)</th><th>at 30 (68° F)</th><th></th></tr></thead><tbody><tr><td>Min:</td><td>48</td><td>16</td><td>12</td><td>(hours)</td></tr><tr><td>Max:</td><td>14</td><td>7</td><td>7</td><td>(days)</td></tr></tbody></table>		at 5 (41° F)	at 20 (68° F)	at 30 (68° F)		Min:	48	16	12	(hours)	Max:	14	7	7	(days)
	at 5 (41° F)	at 20 (68° F)	at 30 (68° F)													
Min:	48	16	12	(hours)												
Max:	14	7	7	(days)												

### NOTES

1. Remove completely all dirt,grease,oil,or other contaminants from surface to be coated.
2. Stir thoroughly the material until it is of uniform constituency prior to application.

;

nd