



Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

OSAKA OFFICE:6-1-124,NISHIKUJYO,KONOHANA-KU,OSAKA 554-0012 JAPAN
TEL No.06-6466-6690 FAX No.06-6466-7797



For more or latest information please consult DNT

Apr. 2007

FEATURES: <ul style="list-style-type: none">· Excellent Adhesivenss.· Good Alkali Resistance.· Good Water Resistance.	NO./NAME :
	MIGHTY ICHIEKI EPO SEALER
	TYPE :
	One-component Epoxy Resin Sealer
	SHIPPING WEIGHT :
	15kg

SPECIFICATION DATA

PACKAGE	1 Component
COLOR	Clear
FINISH	-
SPECIFIC GRAVITY at 20	Material : 0.85 Volatiles : 0.80
VISCOSITY at 20	-
SOLIDS CONTENT	14 ~ 18% - by weight
DRYING TIME	at 5 at 20 at 30 (41° F) (68° F) (68° F)
	To Touch : 60 30 20 (minutes)
	Tack Free : 8 3 2 (hours)
	The recoating time is specified in the application instructions.
RECOMMENDED DRY FILM THICKNESS PER COAT	-
FLASH POINT	41 (106 ° F)
SHELF LIFE at 20	1 Year

DNT Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

MIGHTY ICHIEKI EPO SEALER

APPLICATION INSTRUCTIONS

SURFACE PREPARATION	See Note 1															
APPLICATION METHOD	Brush , Roller , Spray															
THINNER REQUIRED	-															
DILUTION RATIO	<u>By Brush , Roller</u> <u>By Spray</u> 0% 0%															
RECOMMENDED FILM THICKNESS PER COAT	Dry: - Wet: 30 μ															
COATING INTERVALS	<table><thead><tr><th></th><th>at 5 (41° F)</th><th>at 20 (68° F)</th><th>at 30 (68° F)</th><th></th></tr></thead><tbody><tr><td>Min:</td><td>8</td><td>3</td><td>2</td><td>(hours)</td></tr><tr><td>Max:</td><td>7</td><td>7</td><td>7</td><td>(days)</td></tr></tbody></table>		at 5 (41° F)	at 20 (68° F)	at 30 (68° F)		Min:	8	3	2	(hours)	Max:	7	7	7	(days)
	at 5 (41° F)	at 20 (68° F)	at 30 (68° F)													
Min:	8	3	2	(hours)												
Max:	7	7	7	(days)												

NOTES

1. Remove completely all dirt,grease,oil,or other contaminants from surface to be coated.
2. Stir thoroughly the material until it is of uniform constituency prior to application.