



Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

OSAKA OFFICE:6-1-124,NISHIKUJYO,KONOHANA-KU,OSAKA 554-0012 JAPAN
TEL No.06-6466-6690 FAX No.06-6466-7797



For more or latest information please consult DNT

Dec. 2004

FEATURES: <ul style="list-style-type: none">· Excellent Workability.· Good Water Resistance.	NO./NAME :
	SUISEI MIGHTY SEALER MULTI
	TYPE : Acrylic Emulsion Sealer.
	SHIPPING WEIGHT : 15kg

SPECIFICATION DATA

PACKAGE	1 Component
COLOR	Blue
FINISH	-
SPECIFIC GRAVITY at 20	Material : 1.05 Volatiles : 1.0
VISCOSITY at 20	12 ~ 14 Seconds(Ford Cup#4)
SOLIDS CONTENT	15% - by weight
DRYING TIME	at 5 at 20 at 30 (41° F) (68° F) (68° F)
	To Touch : 60 30 20 (minutes)
	Tack Free : 4 1.5 1 (hours)
	The recoating time is specified in the application instructions.
RECOMMENDED DRY FILM THICKNESS PER COAT	-
FLASH POINT	-
SHELF LIFE at 20	1 Year

DNT Product Data Sheet

DAI NIPPON TORYO. CO.,LTD.

SUISEI MIGHTY SEALER MULTI

APPLICATION INSTRUCTIONS

SURFACE PREPARATION	See Note 1															
APPLICATION METHOD	Brush, Roller,Airless Spray															
THINNER REQUIRED	Clean Fresh Water															
DILUTION RATIO	<u>By Brush, Roller</u> <u>By Airless Spray</u> 0% 0%															
RECOMMENDED FILM THICKNESS PER COAT	Dry: - Wet: -															
COATING INTERVALS	<table><thead><tr><th></th><th>at 5 (41° F)</th><th>at 20 (68° F)</th><th>at 30 (68° F)</th><th></th></tr></thead><tbody><tr><td>Min:</td><td>4</td><td>2</td><td>2</td><td>(hours)</td></tr><tr><td>Max:</td><td>1</td><td>1</td><td>1</td><td>(months)</td></tr></tbody></table>		at 5 (41° F)	at 20 (68° F)	at 30 (68° F)		Min:	4	2	2	(hours)	Max:	1	1	1	(months)
	at 5 (41° F)	at 20 (68° F)	at 30 (68° F)													
Min:	4	2	2	(hours)												
Max:	1	1	1	(months)												

NOTES

1. Remove completely all dirt,grease,oil,or other contaminants from surface to be coated.
2. Stir thoroughly the material until it is of uniform constituency prior to application.