



DNT

OSAKA OFFICE: 6-1-124. NISHIKUJO. KONOYAMA-KU. OSAKA 554-0012 JAPAN TEL. NO. 06-6466-6626

FAX. NO. 06-6468-1408

TOKYO OFFICE: 5-13-23. KAMATA. OHTA-KU. TOKYO 144-0052 JAPAN TEL. NO. 03-5710-4502

DAI NIPPON TORYO CO.,LTD.

COMPOSITION & CHARACTERISTICS

Product Name : **ZETTAR SUPER**
Standard : **Standard inside the firm**
Composition :

Zinc powder	69.0
Epoxy ester resin varnish	14.0
Additive	2.0
Solvent	15.0
<hr/>	
Total	100.0 (wt. %)

Note : The values above are mean,
so some allowable variation may occur.

Characteristics :

<u>Test items</u>	<u>Requirements</u>	<u>Average of observed values</u>
Condition in container	Good	Good
Specific gravity (20 °C)	2.3 ± 0.2	2.3
Working properties	Good	Good
Drying time (h) (Tack free)	Within 1(20 °C)	Good
Appearance of film	Good	Good
Impact resistance(500mm, 500g)	Good	Good
Water resistance (72h)	Good	Good
Salt water resistance (72h)	Good	Good
Solid content (wt.%)	Over 70	78
Metallic zinc content in solid content (wt.%)	Over 70	81