



DNT

OSAKA OFFICE: 6-1-124. NISHIKUJO. KONOYAMA-KU. OSAKA 554-0012 JAPAN TEL. NO. 06-6466-6626

FAX. NO. 06-6468-1408

TOKYO OFFICE: 5-13-23. KAMATA. OHTA-KU. TOKYO 144-0052 JAPAN TEL. NO. 03-5710-4502

DAI NIPPON TORYO CO.,LTD.

COMPOSITION & CHARACTERISTICS

Product Name : DNT UNIVERSAL PRIMER Color : Red oxide
Standard : Standard inside the firm
Composition :

Anticorrosive pigment	13.0
Tinting & Extender Pigment	27.0
Epoxy ester resin varnish	50.0
Additive	2.5
Solvent	7.5
<hr/>	
Total	100.0 (wt. %)

Note : The values of the composition are mean,
so some allowable variation may occur.

Characteristics :

<u>Test items</u>	<u>Requirements</u>	<u>Average of observed values</u>
Condition in container	Good	Good
Fineness of grind (microns)	Within 50	20
Working properties	Good	Good
Drying time (h) (Tack free)	Within 6	Good
Appearance of film	Good	Good
Salt water resistance (3 w/v %, 96 hrs.)	Good	Good
Overcoatability	Good	Good
Solid content (wt. %)	Over 55	60

2008.09

