



DNT

OSAKA OFFICE: 6-1-124. NISHIKUJO. KONOYAMA-KU. OSAKA 554-0012 JAPAN TEL. NO. 06-6466-6626

FAX. NO. 06-6468-1408

TOKYO OFFICE: 5-13-23. KAMATA. OHTA-KU. TOKYO 144-0052 JAPAN TEL. NO. 03-5710-4502

**DAI NIPPON TORYO CO.,LTD.**

## COMPOSITION & CHARACTERISTICS

Product Name : RUBBER TIGHT #100 UNDERCOAT  
Standard : Standard inside the firm  
Composition :

Anticorrosive pigment	16.0
Tinting & Extender pigment	24.0
Chlorinated rubber resin varnish	40.0
Alkyd resin varnish	10.5
Additive	1.5
Solvent	8.0
<hr/>	
Total	100.0 (wt. %)

Note : The values above are mean,  
so some allowable variation may occur.

Characteristics :

<u>Test items</u>	<u>Requirements</u>	<u>Average of observed values</u>
Condition in container	Good	Good
Working properties	Good	Good
Drying time (h) (Tack free)	Within 6(20°C)	Good
Appearance of film	Good	Good
Overcoatability	Good	Good
Adhesive property for recoat	Good	Good
Bending resistance (6mm mandrel)	Good	Good
Salt water resistance (168h)	Good	Good
Solid content (wt. %)	Over 50	65
Matter insoluble in solvent (wt. %)	Over 35	40
Qualitative analysis of matter soluble in solvent (wt. %)	Chlorine	Good

