



DNT

OSAKA OFFICE: 6-1-124. NISHIKUJO. KONOYAMA-KU. OSAKA 554-0012 JAPAN TEL. NO. 06-6466-6626

FAX. NO. 06-6468-1408

TOKYO OFFICE: 5-13-23. KAMATA. OHTA-KU. TOKYO 144-0052 JAPAN TEL. NO. 03-5710-4502

DAI NIPPON TORYO CO.,LTD.

COMPOSITION & CHARACTERISTICS

Product Name : **RUBBER TIGHT #100 TOP COAT SILVER**
Standard : **Standard inside the firm (chlorinated rubber aluminium paint)**
Composition :

(Paste)	Aluminium paste	25.0
	Total	25.0
(Base)	Chlorinated rubber resin varnish	69.0
	Additive	1.0
	Solvent	5.0
	Total	75.0
	Sum Total	100.0 (wt. %)

Note : The values of the composition are mean,
so some allowable variation may occur.

Characteristics :

<u>Test items</u>	<u>Requirements</u>	<u>Average of observed values</u>
Condition in container	Good	Good
Miscibility	Good	Good
Specific gravity (20)	Below 1.30	1.20
Working properties	Good	Good
Drying time (h) (Tack free)	Within 5(20)	Good
Contrast ratio	Over 0.90	1.00
Adhesive property for recoat	Good	Good
Bending resistance (10mm mandrel)	Good	Good
Specular gloss (60 ° /60 ° , %)	Over 70	100
Solid content (wt. %)	Over 45	53
Matter insoluble in solvent (wt. %)	Within 35	16
Accelerated weathering resistance	Good	Good