



Product Data Sheet

DAI NIPPON TORYO CO.,LTD.
OSAKA OFFICE: ADDRESS:6-124,NISHIKUJYO,KONOHANA-KU,OSAKA 554 JAPAN
TEL.No.06-6466-6600 FAX No.06-6466-7797



For more or latest information please consult DNT.

Nov. 2008

FEATURES:

- ◆ Low temperature type.
- ◆ Chrome and lead pigments are not contained.

NAME:

No.3430

DELICON LB#110

TYPE:

Melamine alkyd resin paint.

SHIPPING WEIGHT:


4Kg , 16Kg

SPECIFICATION DATA

◆PACKAGE	1 Component
◆COLOR	Full range color
◆FINISH	Full range gloss
◆SPECIFIC GRAVITY @20°C	Material : 1.19 (Pale color) Volatiles : 0.88
◆VISCOSITY @20°C	100 seconds. (Ford Cup No.4)
◆SOLIDS CONTENT	65% - by weight (Pale color)
◆BAKING CONDITIONS	110°C (230°F) - 20minutes.
◆RECOMMENDED DRY FILM THICKNESS PER COAT	25±5 Microns
◆SHELF LIFE @20°C	6 Months.

The above data indicates the average under normal conditions and may vary slightly depending on the conditions.

◆CONTROL RANGE OF BAKING CONDITION (Atmosphere temp. in oven)



The above baking condition is based on thin steel panel. (0.6~0.8mm)